Amendments to the claims:

This listing of claims will replace all prior versions, and listings of claims in the application.

Listing of Claims:

- Claim 1. (Previously Presented) An amorphous shape memory polymeric network comprising a crosslinked ABA triblock dimethacrylate macromonomer, wherein the macromonomer comprises blocks derived from polyesters and polyethers, and wherein A blocks of the ABA triblock have a molecular weight of 1500 g/mol to 3200 g/mol.
- Claim 2. (Previously Presented) The amorphous network according to claim 1, wherein the polyester is a poly (rac-lactide).
- Claim 3. (Previously Presented) The amorphous network according to claim 1, wherein the polyester is the A block.
- Claim 4. (Currently Amended) The amorphous network according to claim 1, wherein the polyether polyester is a polypropylene oxide.
- Claim 5. (Currently Amended) The amorphous network according to claim 1, wherein the polyether polyester is the B block.
- Claim 6. (Currently Amended) A method for preparing the an amorphous polymeric network of claim 1, comprising irradiating a melt comprising an ABA triblock dimethacrylate macromonomer as defined in claim 1 with UV light in order to induce crosslinking of the macromonomer.

Claims 7-10. (Canceled).

- Claim 11. (Previously Presented) An amorphous shape memory polymeric network comprising a crosslinked ABA triblock dimethacrylate macromonomer, wherein the macromonomer comprises blocks derived from polyesters and polyethers, and wherein the amorphous network has a recovery value of above approximately 90%.
- Claim 12. (Previously Presented) An amorphous shape memory polymeric network comprising a crosslinked ABA triblock dimethacrylate macromonomer, wherein the

PATENT
Attorney Docket No. 26538-0012
U.S. Patent Application No. 10/534,937
Response to Office Action dated August 29, 2007

macromonomer comprises blocks derived from polyesters and polyethers, and wherein the amorphous network is completely amorphous.